



Printing Binder

Colour and Appearance	Milky White liquid.
Composition	Self cross linking acrylic co-polymer
pH	7 ± 1
Solubility in water	Soluble.
Active contents	35 ± 1%
Solid contents	37 ± 1%
RO Water (Steam condensed/D.M.)	83.4 to 88.5
Liq NH3	0.5 to 0.7
Gunj Print-200 Thickener	1.2 to 1.25
MJ - 370 Binder	6 to 8
Pigment	2.0 to 3.0