



**Vam Veova Binder**

Product	Solid Content	Viscosity	MFFT	Recommended Application
VISIMER 4954 E	55± 1	1000 - 2500 cps	13°C	Ter Polymer with Good Scrub and Exterior Durability
VISIMER 4955E	55± 1	3000 – 5000 cps	13°C	High Soild Ter-Polymer with excellent Scrub and Exterior Durability